10

15

What is Claimed is

wherein the vital matter is prepared by the following steps: 1) preparing a composition containing kaoline (white soil) 30.0-40.0wt%, potassium sulfate 15.0-20.0wt%, sodium sulfate 13.0-17.0wt%, feldspar 12.0-16.0wt%, talc 12.0-16.0% and ferric oxide 0.5-1.5wt% (step 1); and 2) mixing the above-mentioned compositin using a compressed molding method (step 2); and 3) heating the mixed composition at 1000-1300°C (step3).

2. The vital matter and the producing method thereof according to claum 1, wherein potassium sulfate and sodium sulfate are replaced by the same ratio of each molecular weight of sodium chloride and sodium chloride.

The vital matter and the producing method thereof according to claim 1, wherein the vital matter is composed of potassium 19.06=23.29wt%, calcium 14.21-17.36wt%, sodium 12.30-14.97wt%, magnesium 11.98-14.64wt%, silicon 13.74-16.80wt%, aluminium 12.21-15.13wt%, iron 3.48-4.26wt%, titanium 0.95-1.17wt%, manganese 0.28-0.40wt%, zinc 0.17-0.20wt%, germanium 0.07-0.09wt%, selenium 0.03-0.04wt% and other elements 1.36-1/67wt%.

4. The vita matter and the producing method thereof



according to claim 1 wherein a composition of the vital matter is used in combination with synthetic resins after prepared in form of minute powder of 200-350 mesh.

5

ally